

TDS n°13 Rev n°1 23/08/2016 Date of Edition: 11/5/2025

B 720 Silver Brazing Alloys Cadmium Free

Mechanical & Physical Properties							
Melting Range	C°	778					
Recommended Working Temperature	C°	778					
Tensile Strength	Мра	-					
Electrical Conductivity	% IACS	87					
Density	gr/cm³	9,06					
Elongation	%	-					

Specifications	
EN ISO 17672	Ag 272
DIN 8513	L-Ag72
AWS A5.8	B-Ag8
DIN EN 1044	AG 401
EN ISO 3677	B-Ag72Cu-780

Main elements % (min-max)

Ag: 71-73 / Cu: 27-29

Other %

Impurity: 0,15 max

Elongation %

RoHS Limit ppm

Cd (100ppm); Pb / Hg / Cr (1000ppm)

Availability							
Bare rods	Coated Rods	Wire / Coil	Foil	Preforms	Powder	Paste	Flexible Wire
•	•	•	•	•	0	0	•

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.

Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A Veliköy / Çerkezköy / Tekirdağ / Turkey 59500 Phone: +90 282 746 1004