B 720
Silver Brazing Alloys Cadmium Free

Mechanical & Physical Properties		
Melting Range	C°	778
Recommended Working Temperature	C°	778
Tensile Strength	Mpa	-
Electrical Conductivity	% IACS	87
Density	gr/cm³	9,06
Elongation	%	-

Specifications		
EN ISO 17672		Ag 272
DIN 8513		L-Ag72
AWS A5.8		B-Ag8
DIN EN 1044		AG 401
EN ISO 3677		B-Ag72Cu-780

Main elements %(min-max)

Ag : 71-73 / Cu : 27-29

Other %

Impurity : 0,15 max

Elongation %
-

RoHS Limit ppm
Cd (100ppm) ; Pb / Hg / Cr (1000ppm)

Availability

Bare rods	Coated Rods	Wire / Coil	Foil	Preforms	Powder	Paste	Flexible Wire
●	●	●	●	●	○	○	●

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.
Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A
Veliköy / Çerkezköy / Tekirdağ / Turkey 59500
Phone: +90 282 746 1004
www.asakaynak.com
info@asakaynak.com