# CUP 700
## Copper - Phosphorus

| Mechanical & Physical Properties | | |
|---|---|---|
| Melting Range | C° | 710-805 |
| Recommended Working Temperature | C° | 730 |
| Tensile Strength | Mpa | |
| Electrical Conductivity | % IACS | 7,5 |
| Density | gr/cm³ | 7,9 |
| Elongation | % | |

| Specifications | | |
|---|---|---|
| EN ISO 17672 | | CuP 180 |
| DIN 8513 | | L-CuP7 |
| AWS A5.8 | | BCuP-2 |
| DIN EN 1044 | | CP 202 |
| EN ISO 3677 | | B-Cu93P-710/805 |

| Main elements %(min-max) |
|---|
| P: 6,8-7,2 / Cu: Bal. |

| Other % |
|---|
| Impurity : 0,25 max |

**RoHS Limit ppm**
Cd (100ppm) ; Pb / Hg / Cr (1000ppm)

| Availability | | | | | | | |
|---|---|---|---|---|---|---|---|
| Bare rods | Coated Rods | Wire / Coil | Foil | Preforms | Powder | Paste | Flexible Wire |
| ● | ○ | ● | ○ | ○ | ○ | ○ | ● |

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

**ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.**
Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A
Veliköy / Çerkezköy / Tekirdağ / Turkey 59500
Phone: +90 282 746 1004
www.asakaynak.com
info@asakaynak.com